

### SealBoss® 1570 LV Applications

SealBoss® 1570 LV WaterStopFom for infiltrating water:

- Hairline Crack Injection
- Defective Concrete (Cracked or Honeycombed)
- Concrete Construction Joints & Cracks
- Brick Construction, Geo Formations
- Pipe Intrusions
- Waste Water Tanks, Water Reservoirs
- Tunnels, Dams, Soil Stabilization
- Sewers, Manholes, Utility Boxes

### Product Description

**SealBoss® 1570 LV WaterStopFom** mixed with **SealBoss® 15x Accelerator** is a super low viscosity, flexible, hydrophobic, water-activated (hydro-active), water cut-off grout and foam seal grout based on MDI polyurethane. The resin is 100% solvent free and 100% solids. The gel-time of the product is adjustable by the mandatory adding of a minimum of 10% SealBoss® 15x Accelerator and a maximum of 20% SealBoss® 15x Accelerator. SealBoss® 1570 LV WaterStopFom is NSF/ANSI Drinking Water Contact Approved.

Upon contact with water SealBoss® 1570 LV WaterStopFom reacts to a flexible foam while expanding its volume 8 to 25 times. The cured material is of a constant volume. Since water is not a component of the foam structure, the cured material is essentially not effected by water or dryness. The reacted material does not shrink or swell.

Depending on the amount of accelerator added, the injection pressures, structure and confinement properties, SealBoss® 1570 LV WaterStopFom reacts to a dense, closed cell, semi flexible product.

SealBoss® 1570 LV WaterStopFom is designed for sealing seeping water leaks and for cutting off water in cracks and joints. Due to the low viscosity of the material, SealBoss® 1570 LV WaterStopFom offers superior penetration in hairline crack injection. The product is suitable for the filling of spaces, cracks and honeycombing in stone or concrete structures. To achieve most satisfying and permanent results in certain applications, a combination of SealBoss® 1570 LV WaterStopFom with other systems of our product line may be advised. Ask your SealBoss technician for details. The product is for professional use.

### Installation Guidelines

SealBoss® 1570 LV WaterStopFom and the SealBoss® 15X Accelerator are supplied separately to allow adjustment of gel-time and to provide a long shelf life. It is mandatory to add SealBoss® 15X Accelerator to ensure a complete reaction as designed. A higher percentage of Accelerator added will increase reactive speed, expansion volume and will lower the density of the product accordingly. The accelerator system offers a very flexible range of reactive properties, gel-time and expansion rate which make this product extremely versatile for many applications. Since the end product is of cellular structure, a higher density is favored for best waterproofing properties. Recommended mix ratios are between 10% and 20% of Accelerator added. In situations of high water flow rates and /or low temperatures, ratios may be increased to 20%. For hairline crack injection and soil stabilization ratios may be lowered to 10%. Observe temperature and humidity of the environment, since

### Water Activated, Polyurethane Waterstop & Seal Flexible Injection Foam Grout

SealBoss® 1570 LV WaterStopFom Advantages:

- SealBoss® Product-Pump-Packer System Solution
- 90 CPS Super Low Viscosity
- Unregulated For Transport
- MDI Formula
- Minimum 10% Accelerator Required

both determine the pot-life of the premixed batch. Do not mix more material than the amount that will be pumped within reasonable time. Rule of thumb: High temperatures and high humidity decreased gel-time.

SealBoss® 1570 LV WaterStopFom reacts with the moisture in the structure and does not need large amounts of water to react. Simultaneous injection of water is typically not necessary. If the area of application seems to be completely dry, pre-injection of water may be recommended in some circumstances.


All equipment, pumps and hoses must be dry. Avoid moisture contact with the mixture to prevent premature reaction. If product foams while pumping, immediately shut down the machine and flush with a cleaner to avoid built up and clogging of the equipment.

### Maintenance of Equipment

**SealBoss® R70 Pump Flush** is a solvent free, non-flammable cleaner, lubricator, pump and hose conditioner. Remove all excess product and any smears. Tools and mixing equipment must be cleaned immediately after use. Cured product is hard to remove. First Step, and only if in compliance with all applicable regulations on the jobsite: Flush with a very small amount of approved solvent. Observe all hazard warnings. Second Step: Flush with SealBoss® R70 Pump Flush circulate cleaner through pump and hoses for several minutes at higher flow rates.

### Health and Safety

Protect your health! always use safety gear in compliance with OSHA and all applicable local and job-site regulations While working with products. Handling of this product may result in spills, splashes, and airborne substances. Wear appropriate safety goggles, gloves and safety clothing at all times. During the pressure injection process a full face shield is advised for anybody within reach of product spill or blowout. Consider property in proximity of the application to prevent loss or damage. Protect jobsite from unauthorized persons. Store all materials and equipment safely and out of reach of children and animals! Observe container labels, SDS, applicable laws and regulations and all instructions before using the product and equipment. In case one of the components comes in contact with the skin, wash thoroughly with soap and water. Provide adequate ventilation in volume and pattern in working area. Further protection: emergency showers and eyewash stations. Get immediate medical attention as needed.



### Technical Properties

|                                                                                                        | 1570 LV WaterStopFoil                                                                                                            | 15X Accelerator                                                                         |
|--------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------|
| Appearance                                                                                             | Amber                                                                                                                            | Clear                                                                                   |
| Solids                                                                                                 | 100%                                                                                                                             | 100%                                                                                    |
| Density, lb/gal - g/ml                                                                                 | 8.9 / 1.1                                                                                                                        | 0.93                                                                                    |
| Boiling Point, °C / °F                                                                                 | 205°C / 400°F                                                                                                                    | 170°C / 338°F                                                                           |
| Flash Point, °C / °F                                                                                   | 180°C / 356°F                                                                                                                    | 125°C / 225°F                                                                           |
| Viscosity, cps                                                                                         | ~ 90 mixed                                                                                                                       | 20                                                                                      |
| Mixing Ratio<br>by Volume<br>(2%-10% accelerator)                                                      | 50-5 parts                                                                                                                       | 10%-20%                                                                                 |
| Solubility in Water                                                                                    | not                                                                                                                              |                                                                                         |
| Packaging                                                                                              | 1 gal<br>5 gal<br>55 gal                                                                                                         | 0.1 gal<br>0.5 gal                                                                      |
| Storage / Shelf Life                                                                                   | Unopened Containers Only<br>at 15-30°C / 58-85°F<br>in dry, sun free indoors<br>2 years - 5 gal / 55 gal<br>1 year - 1 gal units | Unopened Containers Only<br>at 15-30°C / 58-85°F<br>in dry, sun free indoors<br>2 years |
| <b>Reaction</b>                                                                                        |                                                                                                                                  |                                                                                         |
| Induction Time, 20°C/68°F                                                                              | 35 sec (10% 15X added)                                                                                                           |                                                                                         |
| Gel time, 20°C/68°F                                                                                    | 140 sec (10% 15xs added)                                                                                                         |                                                                                         |
| <b>Properties Cured</b>                                                                                |                                                                                                                                  |                                                                                         |
| Physical properties<br>may vary based on water<br>& accelerator ratios<br>& conditions during reaction |                                                                                                                                  |                                                                                         |
| Expansion, %                                                                                           | 600-2500 (6-25 Times) depending on Accelerator ratio & counter pressure                                                          |                                                                                         |
| Elongation, %                                                                                          | 250                                                                                                                              | ASTM D 638                                                                              |
| No ASTM D1042 Shrinkage                                                                                | <4%                                                                                                                              | ASTM D1042                                                                              |
| Tensile Strength                                                                                       | 100-120 psi                                                                                                                      | ASTM D 638                                                                              |
| Shrinkage                                                                                              | <4%                                                                                                                              | ASTM D 1042                                                                             |
| Strength (Sand Filled)                                                                                 | 1550 psi                                                                                                                         |                                                                                         |
| Corrosiveness                                                                                          | Non-Corrosive                                                                                                                    |                                                                                         |
| Appearance                                                                                             | Yellowish-White Polyurethane Foam                                                                                                |                                                                                         |
| Toxicity                                                                                               | MDI Based, Good Resistance to Chemicals<br>Resistant to Most Organic Solvents,<br>Mild Acids, Alkali and Micro Organisms         |                                                                                         |



**Limited Warranty Policy and Disclaimer for Products Supplied and/or Distributed by SealBoss Corp.:** SealBoss Corp. Products are for Professional Use. All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use. SealBoss Corp. warrants supplied / distributed products to be free of manufacturing defects. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of the manufacturer which proves to be defective. There are no other warranties by SealBoss Corp. of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. SealBoss Corp. shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. SealBoss Corp. shall not be responsible for use of this product in a manner to infringe on any patent or any other intellectual property rights held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, UV damage, excessive temperature exposure, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and / or physical movement of the substrate or structural defects are also excluded from the limited warranty. SealBoss Corp. reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations and statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. SealBoss Corp. reserves the right to change the properties of products without notice.

Revised 201707