

### Polyurethane Foam Resin For

### Wet & Dry

### Injection Applications

### SealBoss® 1503 Applications

#### SealBoss® 1503 Water Stop Foam Advantages:

- Fast Curing With and Without Water
- Fast Sealing Foam Structure Upon Contact With Water
- Low viscosity, Flexible After Cure
- Universally Applicable
- Fast Curing – Permanent Seal
- For Professional Use Only

#### SealBoss® 1503 Water Stop Foam for infiltrating water:

- Defective Concrete (Cracked or Honeycombed)
- Concrete Construction Joints & Cracks
- Brick Construction, Geo Formations
- Pipe Intrusions
- Waste Water Tanks, Water Reservoirs
- Tunnels, Dams, Soil Stabilization
- Sewers, Manholes, Utility Boxes

### Product Description

**SealBoss® 1503 Foam Resin** is a Flexible Hydrophobic Foam and Resin Combination Product.

#### Dry:

In a dry environment the material will behave like a low viscosity resin and cure to a flexible non cellular sealant.

#### Wet:

When in contact with water the product will react like a hydro-active polyurethane foam and expand and cure to a flexible foam.

Since water is not a component of the cured product's structure, the applied material is essentially not effected by water or dryness. The reacted material does not shrink or swell. The MDI polyurethane based resin is 100% solvent free and 100% solids.

Due to the low viscosity of the material, SealBoss® 1503 Foam Resin offers superior penetration in hairline crack injection. The product is suitable for the filling of spaces, cracks and honeycombing in stone or concrete structures. Ask your SealBoss® technician for details. The product is for professional use.

### Installation Guidelines

**SealBoss® 1503 Foam Resin is an extremely versatile leak seal product as it can be applied in wet, damp and completely dry environments.**

Continue the injection until resin leaks out from the cracks and/or from the adjacent packers. This is necessary to get an even material distribution

All equipment, pumps and hoses however must be dry. Avoid moisture contact with the mixture to prevent premature reaction. If product foams while pumping, immediately shut down the machine and flush with a cleaner to avoid built up and clogging of the equipment.

### Maintenance of Equipment

Tools and equipment must be cleaned immediately after use. Remove all excess product. Cured product is hard to remove.

**SealBoss® R70 Pump Flush** is a solvent free, non-flammable cleaner, lubricator, pump and hose conditioner. Please refer to the product data sheet for detailed information.

### Health and Safety

Protect your health! Always use safety gear in compliance with OSHA and all applicable local and job-site regulations While working with products. Handling of this product may result in spills, splashes, and airborne substances. Wear appropriate safety goggles, gloves and safety clothing at all times. During the pressure injection process a full face shield is advised for anybody within reach of product spill or blowout. Consider property in proximity of the application to prevent loss or damage. Protect jobsite from unauthorized persons. Store all materials and equipment safely and out of reach of children and animals! Observe container labels, SDS, applicable laws and regulations and all instructions before using the product and equipment. In case one of the components comes in contact with the skin, wash thoroughly with soap and water. Provide adequate ventilation in volume and pattern in working area. Further protection: emergency showers and eyewash stations. Get immediate medical attention as needed.

## 1503 Foam Resin Wet & Dry Reactive Combi Foam

### Technical Properties

	1503 Foam Resin Comp. A	1503 Foam Resin Comp. B
Appearance	Amber	Amber
Solids	100%	100% ASTM D 1010
Density, lb/gal - g/ml	1.0	1.1 ASTM D 3800-79
Mixing Ratio by Volume (2%-10% accelerator)	50-10 parts	1 part
Solubility in Water	not	
Packaging	1 gal 5 gal	1 gal 5 gal
Storage / Shelf Life	Unopened Containers Only at 15-30°C / 58-85°F in dry, sun free indoors 2 years - 5 gal / 55 gal 1 year - 1 gal units	Unopened Containers Only at 15-30°C / 58-85°F in dry, sun free indoors 2 years

### A/B Combined Data

Viscosity, cps	300-350	ASTM D 2196
<b>Reaction</b>		
Induction Time, 20°C / 68°F	55 sec	
Gel time, 21°C / 70°F	200 sec	

### Properties Cured

Physical properties may vary based on water & accelerator ratios & conditions during reaction	
Expansion, %	1000-1200 (10-12 Times)
Elongation, %	>10 % ASTM D 638
Adhesive Strength	~ 0.3 N/mm2 ~50 psi ASTM D 638
Hardness Shore A	~ 45-50
Corrosiveness	Non-Corrosive
Appearance	Yellow-White Polyurethane Foam
Toxicity	MDI Based, Good Resistance to Chemicals Resistant to Most Organic Solvents, Mild Acids, Alkali and Micro Organisms



**Limited Warranty Policy and Disclaimer for Products Supplied and/or Distributed by SealBoss Corp.:** SealBoss Corp. Products are for Professional Use. All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use. SealBoss Corp. warrants supplied / distributed products to be free of manufacturing defects. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of the manufacturer which proves to be defective. There are no other warranties by SealBoss Corp. of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. SealBoss Corp. shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. SealBoss Corp. shall not be responsible for use of this product in a manner to infringe on any patent or any other intellectual property rights held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, UV damage, excessive temperature exposure, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and / or physical movement of the substrate or structural defects are also excluded from the limited warranty. SealBoss Corp. reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations and statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. SealBoss Corp. reserves the right to change the properties of products without notice.

Revised 202002